

# A comparison study of fatigue behavior in Al-Al and Al-steel refill friction stir spot welding joint

Haokun Yang<sup>1</sup>, Detao Cai<sup>2</sup>, Jiaxin Li<sup>1</sup>, ChinYung Kwok<sup>1</sup>, yunqiao Zhao<sup>2</sup>, Yu Li<sup>2</sup>, haisheng Liu<sup>2</sup>, and waiwah Lai<sup>1</sup>

<sup>1</sup>Hong Kong Productivity Council

<sup>2</sup>Guangdong Academy of Sciences

May 31, 2021

## **A comparison study of fatigue behavior in Al-Al and Al-steel refill friction stir spot welding joint**

Haokun Yang<sup>1a\*</sup>, Detao Cai<sup>2,3a</sup>, Jiaxin Li<sup>1</sup>, Chin Yung Kwok<sup>1</sup>, Yunqiang Zhao<sup>3</sup>, Yu Li<sup>4</sup>, Haisheng Liu<sup>4</sup>, Waiwah Lai<sup>1</sup>

1 Smart Manufacturing Division (SMD), Hong Kong Productivity Council (HKPC), Hong Kong 999077, People's Republic of China

2 State Key Laboratory of Advanced Design and Manufacturing for Vehicle Body, Hunan University, Changsha, Hunan 410082, People's Republic of China

3 China-Ukraine Belt and Road Joint Laboratory on Materials Joining and Advanced Manufacturing, China-Ukraine Institute of Welding Guangdong Academy of Sciences, Guangzhou, Guangdong 510650, People's Republic of China

4 Center for Industrial Analysis and Testing, Guangdong Academy of Science, Guangzhou, Guangdong 510650, People's Republic of China

a These authors contribute equally

Corresponding author: Haokun Yang, +852 27885679, [hkyang@hkpc.org](mailto:hkyang@hkpc.org)

Keywords: Refill friction stir spot welding, Fatigue fracture, Aluminum, Steel

## **1. Introduction**

Lightweight is one of the most important directions in the global development of new energy mobility [1]. Several concepts were developed as: (1) Hybrid sandwich metal-plastic structure [2]; (2) High strength alloys [3, 4]; (3) Material joining, e.g. self-piercing riveting (SPR) [5], electric resistance welding (ERW) [6] and friction stir welding (FSW) [7].

FSW has achieved outstanding welding properties, but the key-holes within the joint will bring in a weak bonding interface [8] and poor mechanical stability [9]. To overcome the above challenges, refill friction stir spot welding (RFSSW) was proposed and developed [10], which works on similar Al-Al and dissimilar Al-steel metallic joints [7], as well as metal-polymer composites [11]. However, the fatigue behavior of the similar and dissimilar material joints fabricated by RFSSW are seldom examined. As the physical properties between Al and steel are different, the joint interface shall have different effects on the fatigue behavior. The present research shall accelerate the design of similar and dissimilar materials joining under RFSSW process.

## 2. Experimental procedure

The studied materials include Aluminum (Al 1060) and steel (DIN 1623) sheets, cleaned and grinded, with thickness of 2.0 mm and area of 50 x 150 mm. The welding was conducted using RFSSW machine provided by Aerospace Engineering Equipment (Suzhou) Co., Ltd. The critical processing parameters are: (1) rotation speed: 2000 RPM; (2) penetration depths 2.40 and 1.85 mm for Al-Al and Al-steel joints; (3) penetration speed: 1 mm/s.

After welding, the cross-section of Al-Al and Al-steel joints were electron spark cut and polished for optical microscope observation. The hardness test was measured along the welding seam, upper and lower sheets (1 mm distance from the welding seam). The loading is 0.245 N and a dwell time of 10 s. The Al-Al and Al-steel specimens were tensile tested by Zwick/Roell Z250 with a strain rate of 1mm/min. The tension-tension fatigue tests were conducted using sinusoidal wave in load control mode with  $R=0$ , and the testing frequency is 30 Hz by Instron 8801. The stress amplitude ( $\Delta\sigma=(\sigma_{\max}-\sigma_{\min})/2$ ) was set as 0.2, 0.3 and 0.4 of the joint shear strengths ( $\sigma_b$ ) to quantitative analysis and comparison. After the fatigue test, all the specimens were stretched to fracture for observing fatigue damages.

## 3. Results and discussion

The hardness distribution of Al-Al joint is shown in Fig. 1(a). In the regions of welding seam, as well as upper and lower sheets, the hardness value varies from 23 to 28 HV. However, the hardness distribution of the Al-steel joint varies much as displayed in Fig. 1(b). The welding seam and lower steel sheet exhibit higher hardness between 120 and 150HV, while the upper Al sheet's hardness is only about 30 HV, resulting in inhomogeneous hardness distribution.

The static overlap-shear strengths ( $\sigma_b$ ) of Al-Al and Al-steel joints are 4691 N and 3846 N. To quantitatively compare the fatigue behaviors of Al-Al and Al-steel joints, the stress amplitudes ( $\Delta\sigma$ ) were set as 0.2, 0.3 and 0.4 of the joint shear strength. The testing results are illustrated in Figs. 1(c&d), where both the Al-Al and Al-steel RFSSW joints exhibit outstanding fatigue properties, compared with other reported results [12, 13]. It is noted that the Al-steel joint with  $\Delta\sigma/\sigma_b=0.2$  does not suffer obvious damages after  $10^5$  cycles.

### 3.1 Al-Al joint

Figures 2 (a&b) illustrate the detailed OM observation of the fatigue fracture with  $\Delta\sigma/\sigma_b=0.2$ . Two fatigue patterns are found: (1) the fatigue striations exhibit circumference direction along the RFSSW joint, where commonly observed in the front of joint, i.e. the fatigue crack initiation region (Fig. 2(a)); (2) the fatigue striations have the path penetrating the thickness direction, which close to the torn fracture region (Figs. 2(b)).

With  $\Delta\sigma/\sigma_b$  increasing to 0.3 as shown in Figs. 2(c&d), the fatigue striations also exhibit two different types with circumference and thickness directions. However, the fatigue striations along thickness direction get more obvious and these striations approach to the fatigue crack initiation region. With  $\Delta\sigma/\sigma_b$  further increasing to 0.4 (shown in Figs. 2(e&f)), the fatigue striations along thickness direction is detected in both crack initiation and torn fracture regions.

The present observation of fatigue behaviors of Al-Al RFSSW supports that the joint significantly influenced by stress amplitude. The higher stress amplitude results in the fatigue striations along thickness direction get more obvious, which cover the fatigue striations with circumference direction located in the crack initiation region. This fatigue behavior transition shall be attributed to the higher stress concentration around the RFSSW joint., rather than the interface between Al-Al layers.

### 3.2 Al-steel joint

Figures 3(a&b) illustrate the OM observation of both the Al sheet and steel sheet fatigue fractures with  $\Delta\sigma/\sigma_b=0.3$ , respectively. It is found that fatigue striations exist in the edge of the joint, starting from the Al part of the joint. With  $\Delta\sigma/\sigma_b$  increasing to 0.4, the fatigue striations are both found from the Al sheet and steel sheet parts as show in Figs. 3(c&d). The present observation supports that the effect of secrete

hardness distribution within the Al-steel joint plays a more important role in fatigue crack initiation position rather than that of the parameter of  $\Delta\sigma/\sigma_b$  does.

#### 4. Conclusions

The fatigue behavior of Al-Al and Al-steel RFSSW joints are systemically studied, and several conclusions are listed as below:

1. Al-Al RFSSW joint has homogeneous hardness distribution across the welding seam, but Al-steel RFSSW joint has discrete hardness distribution.
2. With stress amplitude or  $\Delta\sigma/\sigma_b$  increasing, the stress concentration within the joint of Al-Al joint grows, resulting in the fatigue striations with thickness direction gets more obvious in the crack initiation region.
3. Regardless of stress amplitude or  $\Delta\sigma/\sigma_b$  varying, Al-steel RFSSW has discrete hardness distribution, leading to fatigue crack initiation from edge of Al-steel joint.

#### Declaration of competing interest

The authors declared that they have no conflicts of interest in this work.

#### Data availability statement

The datasets generated during and/or analysed during the current study are available from the corresponding author on reasonable request.

#### Author Contribution Statement

H.K. and D.T designed the experiments and wrote the manuscript. J.X. and C.Y. performed optical microscope observation. Y. and H.S. carried out the tensile and fatigue test. W.W. helped shape the research, analysis and manuscript.

#### Acknowledgments

The Innovation and Technology Fund (ITF) ITP/021/19AP financially supported this work. Y.H.K. thanks for his wife M.T.'s support on his career during the custom sealing off period between Hong Kong and Shen Zhen in the past 15 months (maybe longer).

#### Reference

- [1] P.L. Threadgill, A.J. Leonard, H.R. Shercliff, P.J. Withers, Friction stir welding of aluminium alloys, *International Materials Reviews* 54(2) (2009) 49-93.
- [2] H. Yang, B.C. Ng, H.C. Yu, H.H. Liang, C.C. Kwok, F.W. Lai, Mechanical properties study on sandwich hybrid metal/(carbon, glass) fiber reinforcement plastic composite sheet, *Advanced Composites and Hybrid Materials* (2021).
- [3] T. Sakai, A. Belyakov, R. Kaibyshev, H. Miura, J.J. Jonas, Dynamic and post-dynamic recrystallization under hot, cold and severe plastic deformation conditions, *Progress in Materials Science* 60 (2014) 130-207.
- [4] H.K. Yang, Y.Z. Tian, Z.F. Zhang, Revealing the mechanical properties and microstructure evolutions of Fe-22Mn-0.6C-(x)Al TWIP steels via Al alloying control, *Materials Science and Engineering: A* 731 (2018) 61-70.
- [5] R. Porcaro, A. Hanssen, M. Langseth, A. Aalberg, Self-piercing riveting process: An experimental and numerical investigation, *Journal of Materials Processing Technology* 171(1) (2006) 10-20.
- [6] H. Zhang, J. Senkara, Resistance welding: fundamentals and applications, CRC press 2011.
- [7] R.S. Mishra, Z. Ma, Friction stir welding and processing, *Materials science and engineering: R: reports* 50(1-2) (2005) 1-78.

- [8] Z. Zhang, Q. Wu, Analytical and numerical studies of fatigue stresses in friction stir welding, *The International Journal of Advanced Manufacturing Technology* 78(9) (2015) 1371-1380.
- [9] J.L. Ju KANG, Zhicao FENG, Guisheng ZOU, Guoqing WANG, Aiping WU, INVESTIGATION ON MECHANICAL AND STRESS CORROSION CRACKING PROPERTIES OF WEAKNESS ZONE IN FRICTION STIR WELDED 2219-T8 Al ALLOY, *Acta Metall Sin* 52(1) (2016) 60-70.
- [10] C. Schilling, J. dos Santos, Method and device for joining at least two adjoining work pieces by friction welding, Google Patents, 2004.
- [11] S.T. Amancio-Filho, C. Bueno, J.F. dos Santos, N. Huber, E. Hage, On the feasibility of friction spot joining in magnesium/fiber-reinforced polymer composite hybrid structures, *Materials Science and Engineering: A* 528(10) (2011) 3841-3848.
- [12] Z. Shen, Y. Ding, J. Chen, A.P. Gerlich, Comparison of fatigue behavior in Mg/Mg similar and Mg/steel dissimilar refill friction stir spot welds, *International Journal of Fatigue* 92 (2016) 78-86.
- [13] A. Kubit, M. Drabczyk, T. Trzepiecinski, W. Bochnowski, Ľ. Kaščák, J. Slotá, Fatigue Life Assessment of Refill Friction Stir Spot Welded Alclad 7075-T6 Aluminium Alloy Joints, *Metals* 10(5) (2020).

### Hosted file

figures\_v3.pdf available at <https://authorea.com/users/416779/articles/524187-a-comparison-study-of-fatigue-behavior-in-al-al-and-al-steel-refill-friction-stir-spot-welding-joint>